

# VERNICE KRISTALL V.10

## Two-component Polyurethane Fast Drying Varnish

### NATURE AND USE

Fast drying varnish formulated for the treatment of wood from impregnation to finish.  
Especially recommended in the Yachting market, for coating systems on wooden boats topsides.

### TECHNICAL DATA



Type of binder:	Polyurethane
Specific gravity A+B:	Kg/l 1,05 ± 0,05 @ +20°C
Solids by Weight:	% 54 ± 3 % A+B
Solids by Volume:	% 45 ± 2 % A+B
Mixing ratio by Weight:	100 parts of Base / 50 parts of Hardener
Mixing ratio by Volume:	2 parts of Base / 1 part of Hardener
**Pot life @ +20°C:	≥ 4 hours
Colour/appearance of the applied film:	Transparent

### SUBSTRATE PREPARATION

#### New wood /brought back to new:

Seasoned and dry (R.H. ≤ 15%), cleaned, sandpapered (P 240-320) and dust free.  
As impregnating agent or first coat: apply the product Thinned by 50%.

For a painting "Open pore" effect @ +20°C, apply 1 – 2 coats of thinned varnish, recoat interval 2 – 4 hours between each coat (Spray application) or 5 – 15 hours (Brush/roller application).  
After 16 – 18 hours, we suggest to sand between each coat with fine-grained abrasive paper P320.

For a painting "Closed pore" effect @ +20°C, apply 8 - 10 coats of thinned varnish, recoat interval 2 - 4 hours between each coat (Spray application) or 5 - 15 hours (Brush/roller application).  
After 16 – 18 hours, we suggest to sand between each coat with fine-grained abrasive paper P320.

#### Wood previously coated:

Wash with soft water. When the substrate is completely dry (R.H. ≤ 15%), check if the varnish and the solvent are compatible with the coats applied below (should any softening appear, remove the old coat of paint down to bare wood, then follow the same instructions given for the new wood), sand with abrasive paper grain P280 -320 and remove all dust.

Apply 2 – 3 coats of product, recoat interval 16 – 18 hours between each coat, sanding from time to time with abrasive paper P 320.

### PRODUCT PREPARATION

Stir separately the Base and the Hardener in their original cans.  
Mix Base and Hardener in the right proportion stirring the mix obtained until a complete homogenization is reached.  
Let the product rest for 10 minutes before applying.

\*\* The "POT LIFE" time of two components products (time within which it is possible to apply the paint mix of Base and Hardener), is exponentially dropped by the increase of product temperature.

Note: The use of a mix of paint (Base + Hardener) over the POT LIFE time is irreparably compromising all the properties of the coating film.\*\*

### APPLICATION DETAILS

Application method:	Conventional spray equipment Roller, brush
---------------------	---

MTDS 03018/ Page 1 of 2

The content of the present technical data sheet is the most complete currently available, based on practical experience and given in good faith. Should any change be necessary, the present data sheet will be updated without prior notice. The applying conditions of use differ according to environmental conditions and subjective application factors outside the control of the Company. The user shall determine the suitability of the product for the intended use under his own risk and responsibility. No warranty is impressed or implied. The Company refuses all liability not directly related with defects of the product or consequent to deviations from written instructions.



INDUSTRIE BRUNO STOPPANI R.P.S. S.r.l.

Sede Operativa: Via Industriale 90-119 25020 Capriano del Colle (Bs) – Italy - Phone +39 030 9745116 – Fax +39 030 9745383

[sales@industri brunostoppa paints.com](mailto:sales@industri brunostoppa paints.com) - [www.industri brunostoppa paints.com](http://www.industri brunostoppa paints.com)

Azienda con sistema di gestione qualità UNI EN ISO 9001:2015 certificato da CISQ/Certiquality - Certificato Nro 2134

# VERNICE KRISTALL V.10

## Two-component Polyurethane Fast Drying Varnish

<b>Thinning:</b>	15 - 30 % Spray application 15 – 20 % Roller or brush application different thinning % can be necessary according to the absorption of the substrate and the thickness required
<b>Thinner:</b>	PUR11 Spray application SINT71 Brush, roller application
<b>Cleaning:</b>	PUR11
<b>Hardening @ + 25°C:</b>	Dust dry 30 - 60 minutes Sandpapering after at least 16-18 hours Full cured 7 days
<b>Recoat interval at + 20°C:</b>	2 – 4 hours Spray application 5 – 15 hours Brush / Roller application
<b>Application Ambient Temperature:</b>	Between +5°C and +35°C
<b>Suggested Temperature of the product:</b>	+20 ÷ +30°C
<b>Substrate Temperature:</b>	+5 / +40°C always at least +3/5°C above dew point
<b>Relative Humidity:</b>	≤ 80%
<b>Suggested thickness:</b>	Dry film thickness 50 - 60µm (open pore) (DFT) applied in 2-3 coats Dry film thickness 175–250 µm (closed pore) (DFT) applied in 8-10 coats
<b>Theoretical spreading rate:</b>	sqm/l 9, 0 per coat at a dry film thickness of 50 µm (DFT)

### HANDLING STORAGE AND SAFETY PRECAUTIONS

**Warning:** All handling and/or use activities of the material and its components must strictly refer to the given indications in the Safety Data Sheet (Base and Hardener). The following advices are stated by common sense and in good faith, they are uncompleted and do not substitute the content of each specific safety data sheet of the product.

**Handling:** The material must be used only by professional and qualified applicators suitably trained. All the operations involving the use of the product, must be carried on in compliance with all the relevant National Health, Safety & Environmental standards and regulations.

**Precautions:** When the product is used in enclosed areas (rooms, containers, vessels, etc.) it is imperative to use adequate means providing the necessary air circulation, to be granted during the whole application and coating polymerization time, also to avoid conditions open to potential explosion danger.

All electrical installations must always be grounded. Where explosion hazards exist, the workmen should be required to use only non-ferrous tools and wear conductive non-sparking shoes and clothing. Explosion and flame-proof equipment too are required.

**Storage and transport:** Keep far from flames, sparks or heat sources. Do not leave exposed under direct solar action. Store under shelter in original unopened packaging, in cool, dry and ventilated areas, at temperatures between +5°C and +35°C.

**Shelf life:** **Base** 12 months in the suggested storage conditions ( original unopened packaging).  
**Hardener** 6 months in the suggested storage conditions ( original unopened packaging).

N.B.: **Product for professional use only and exclusively for the uses not regulated under CE Directive 2004/42/CE.**

**Refer to Material Safety Data Sheet**

MTDS 03018/ Page 2 of 2

The content of the present technical data sheet is the most complete currently available, based on practical experience and given in good faith. Should any change be necessary, the present data sheet will be updated without prior notice. The applying conditions of use differ according to environmental conditions and subjective application factors outside the control of the Company. The user shall determine the suitability of the product for the intended use under his own risk and responsibility. No warranty is impressed or implied. The Company refuses all liability not directly related with defects of the product or consequent to deviations from written instructions.



**INDUSTRIE BRUNO STOPPANI R.P.S. S.r.l.**

**Sede Operativa:** Via Industriale 90-119 25020 Capriano del Colle (Bs) – Italy - Phone +39 030 9745116 – Fax +39 030 9745383

**sales@industri brunostoppa paints.com - [www.industri brunostoppa paints.com](http://www.industri brunostoppa paints.com)**

Azienda con sistema di gestione qualità UNI EN ISO 9001:2015 certificato da CISQ/Certiquality - Certificato Nro 2134